

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B01D 53/94		A1	(11) International Publication Number: WO 99/00177
			(43) International Publication Date: 7 January 1999 (07.01.99)
(21) International Application Number: PCT/GB98/01838		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, GW, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).	
(22) International Filing Date: 24 June 1998 (24.06.98)			
(30) Priority Data: 9713428.2 26 June 1997 (26.06.97) GB			
(71) Applicant (for all designated States except US): JOHNSON MATTHEY PUBLIC LIMITED COMPANY [GB/GB]; 2-4 Cockspur Street, Trafalgar Square, London SW1Y 5BQ (GB).			
(72) Inventors; and (75) Inventors/Applicants (for US only): BRISLEY, Robert, James [GB/GB]; 9 Greenacres, Duxford, Cambridge CB2 4RB (GB). BROGAN, Mark [GB/GB]; 84 Walpole Road, Cambridge CB1 3UE (GB). CLARK, Antony, David [GB/GB]; 25 Suez Road, Cambridge CB1 3QB (GB).			
(74) Agent: WISHART, Ian, Carmichael; Johnson Matthey Technology Centre, Blounts Court, Sonning Common, Reading RG4 9NH (GB).		Published With international search report.	

(54) Title: CATALYTIC CONVERTER FOR A LEAN BURN INTERNAL COMBUSTION ENGINE

(57) Abstract

A layered exhaust gas catalyst containing Pt in a first layer and Rh in a second layer is more selective for catalysing the reaction between NO_x and/or nitrate with hydrocarbons and/or CO than for catalysing the reaction between hydrocarbons and/or CO with oxygen. NO_x can be reduced to N₂ under constant lean to stoichiometric conditions without the need for rich spikes.

CATALYTIC CONVERTER FOR A LEAN BURN INTERNAL COMBUSTION ENGINE

The present invention concerns improvements in emissions control, especially in the control of NOx under lean conditions.

The problems of controlling regulated emissions from internal combustion engines are well known. A particular difficulty is the reduction of NOx to in the case of "lean-burn" motors of various types, because there is generally an excess of oxygen in the exhaust gases, making reduction reactions more difficult. There are commercial and environmental pressures encouraging lean-burn engines, because of their fuel economy. At the same time, however, there are technical pressures such as the difficulty in reduction of NOx already mentioned and the generally cooler exhaust gases caused by excess air in turn making it more difficult to reach temperatures over a catalytic convertor at which adequate conversion takes place.

The best-known approach for NOx conversion for lean-burn engines is applied commercially by the inclusion in the catalyst of a NOx storage component such as Ba, Ca *etc.*, which operates to store NOx during lean operation. The NOx storage component releases absorbed NOx when the oxygen content of the exhaust gas is lowered. For example, EP 560991 describes such a system; lowering of the oxygen content of the exhaust gases is achieved by making the exhaust gases rich or stoichiometric by controlling the air-fuel ratio. Various techniques are available to achieve this, primarily involving designing the engine management system to provide rich "spikes" or excursions during normal lean running. It is our belief that all known practical examples of lean-burn engines incorporating such NOx storage concepts utilise either deliberate engine management strategies which provide $\lambda \geq 1$ excursions according to a predetermined assessment of the approach of saturation of the NOx storage component, or utilise the natural fluctuation of λ greater than 1 upon acceleration or some other part of the engine operating cycle.

In addition to the aforesaid EP 560991, other proposals to treat the exhaust gases from gasoline motors which operate at least predominately in the lean burn region, are

surfaces of the catalyst components) preferentially reacts with gaseous hydrocarbon and/or CO. Desirably, the catalyst components are designed to be deficient in oxygen and/or oxidising species compared to the exhaust gas, under normal running conditions.

5 NOx storage components suitable for use in the present invention include one or more alkali metal or alkaline earth metal compounds.

The present invention makes it possible to operate lean-burn engines of various types, especially direct-injection gasoline engines, constantly in the lean mode. This offers
10 considerable promise in improved fuel consumption and may offer improvements in driveability. Additionally, the fundamentally different approach, relying on a catalyst designed to have the specified selectivity rather than on the storage of NOx, offers the skilled person greater opportunities for catalyst formulation than is the case with a conventional NOx storage catalyst. It will be readily appreciated that a catalyst that depends
15 upon NOx storage will become saturated and will require periodic regeneration. In the present invention, for reasons that are not yet fully understood, NOx does not saturate the catalyst, although there may be, on the molecular level, storage of NOx as nitrate on the surface of certain of the catalyst components.

20 In accordance with the present invention, the catalyst is designed and formulated to achieve the desired selectivity. It is believed that, following the teaching of the present invention regarding the desirability of such selectivity, the skilled person can achieve such selectivity in a number of ways. A suitable catalyst is a supported catalyst with a platinum group metal and a NOx storage component together effective to catalyse the oxidation of NO
25 to NO₂ and/or NO₃ in one layer and a second layer containing a platinum group metal effective to reduce NO to N₂. Preferably, the catalyst comprises a first layer comprising platinum and barium or calcium carried on a high surface area alumina-containing support. Preferably, the second layer of the catalyst comprises rhodium and cerium carried on a high surface area support which does not contain alumina. More preferably, there is no
30 significant quantity of rhodium in the first layer, and no significant quantity of platinum or NOx storage component in the second layer.

variant. A yet further embodiment desirably uses low-sulphur fuel (*eg* less than 50ppm S) and low-sulphur lubricants, *eg* synthetic lubricants rather than those refined from crude oil, together with the novel catalytic convertor of the present invention.

5 The invention is illustrated with reference to the accompanying drawings, in which
Figure 1 is a chart showing emissions from a direct-injection engine fitted with a conventional NOx-trap catalyst, and

Figure 2 is a similar chart for the same engine fitted with a selective catalyst according to the invention.

10

A Mitsubishi Galant GDi was fitted with a conventional commercial high efficiency lean NOx Pt/Rh catalyst supported on an alumina washcoat carried on a 400 cells/ square inch cordeirite monolith. The catalyst formulation contains Ba which acts as a NOx store. The engine is controlled to run lean and at no time does the air/fuel ratio exceed $\lambda = 1$ during the ECE test cycle.

15

Referring to Figure 1, the speed is in the ECE cycle shown as a complex cycle, the accumulative NOx concentration is shown at two positions, before the catalyst ("engine out") and after the catalyst ("tailpipe"). It can be seen that engine out NOx accumulates steadily, whereas after about one minute the catalyst reaches operating temperature and begins to convert NOx to N₂. There is, however, a proportion of NOx which is not converted, so that the cumulative tailpipe emissions also increase constantly.

20


The same motor car was then fitted with an experimental catalyst whose preparation is described in detail below and the same tests performed. The results shown in Figure 2 show, after the initial period, a flat trace of cumulative tailpipe NOx emissions, indicating that all of the NOx emitted from the engine is being converted. Additional studies have shown that the expected NOx storage capacity has been exceeded many-fold. It is interpreted that the experimental catalyst shows unexpected and valuable selectivity for the reaction between NOx and/or nitrate with hydrocarbons and/or CO compared to the reaction between hydrocarbons and/or CO with oxygen. It is also interpreted that the novel catalyst

25

30

CLAIMS

1. A catalytic convertor for a lean-burn engine comprising a catalyst component capable of storing NO_x, characterised in that the catalyst is constructed to incorporate a further catalyst component which exhibits greater selectivity for catalysing the reaction between NO_x and/or nitrate with hydrocarbons and/or CO than for catalysing the reaction between hydrocarbons and/or CO with oxygen.
2. A catalytic convertor for a lean-burn engine, comprising a supported layered catalyst having a first layer containing a first platinum group metal and a NO_x storage component together effective to catalyse the oxidation of NO to NO₂ and/or NO₃ and to store NO₃ as nitrate and further effective to release NO and O₂, and a second layer containing a second, different, platinum group metal, effective to reduce NO to N₂.
3. A catalytic convertor according to claim 2, wherein the first layer contains platinum and the second layer contains rhodium.
4. A catalytic convertor according to claim 3, wherein the first layer contains platinum carried on an alumina-containing washcoat and the NO_x storage component is barium, and the second layer contains rhodium carried on a washcoat which does not contain alumina.
5. A catalytic convertor according to claim 4, wherein the first layer washcoat comprises alumina, ceria and zirconia, optionally as a mixed oxide of two or more thereof, and the second washcoat layer contains ceria and zirconia, optionally as a mixed oxide.
6. A catalytic convertor according to claim 3, wherein the first layer comprises platinum carried on an alumina washcoat which also incorporates potassium, and the second layer comprises rhodium carried on a ceria/zirconia washcoat and an interlayer comprising a washcoat and a barium compound is provided between said first and second layers.



INTERNATIONAL SEARCH REPORT

Interr. Application No

PCT/GB 98/01838

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 B01D53/94

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 B01D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 716 876 A (TOYOTA MOTOR CO LTD) 19 June 1996 cited in the application	1,2, 11-13
Y	see page 2, line 54 - page 4, line 5 see page 4, line 16 - page 6, line 10	4,5,7,8
Y	US 5 459 119 A (ABE FUMIO ET AL) 17 October 1995 see column 2, line 38 - column 5, line 61 see column 8, line 25 - column 15, line 50; tables 1,2	4,5,7,8
A	EP 0 669 157 A (TOYOTA MOTOR CO LTD ;CATALER IND CO (JP)) 30 August 1995 see page 4, line 50 - page 6, line 23; claims 1-22	1-5,7,8, 11,12

☒

Further documents are listed in the continuation of box C.

☒

Patent family members are listed in annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

28 September 1998

Date of mailing of the international search report

07/10/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Cubas Alcaraz, J

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 98/01838

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0716876 A	19-06-1996	JP 8168675 A	02-07-1996
		AU 677534 B	24-04-1997
		AU 4050995 A	27-06-1996
		US 5702675 A	30-12-1997
US 5459119 A	17-10-1995	JP 6233918 A	23-08-1994
EP 0669157 A	30-08-1995	JP 7232064 A	05-09-1995
		AU 670727 B	25-07-1996
		AU 1344195 A	07-09-1995
EP 0771584 A	07-05-1997	JP 9122486 A	13-05-1997
		AU 692118 B	28-05-1998
		AU 7048796 A	03-07-1997